

51.101N | StrongTouch

Features

51.101N | StrongTouch is a matt white 90 micron polymeric vinyl, printable with a broad range of wide format printing methods: (eco)solvent, UV and latex inks. This product is coated with a very high performance acrylic adhesive which allows removing the film for up to 12 months whilst maintaining the ability to stick for longer periods of time.

This makes it an ideal solution for temporary floor signs and decals, or point of purchase advertising on walls and counter tops. StrongTouch will also stick to carpets with a low pile and tight pattern. If used as a floorgraphic, we recommend to combine the 51.101N StrongTouch with our anti-slippery 21.000N | SlipStop 100 overlaminating film. StrongTouch can also be used to create custom whiteboards, in combination with the Total Eraze Clear films.

51.101N | StrongTouch is available in 1370mm (width) x 50m (length) rolls.

Technical & Performance Information

Film Thickness	90 micron
Adhesive Thickness	25 micron
Total Thickness	115 micron
Adhesive type	High tack removable clear solvent based acrylic
Release Liner	140 gsm double-sided PE coated lay-flat kraft liner
Artificial Weathering*	>5 years
Adhesion to steel (20 mins / 180°)	14 N/25mm
Adhesion to steel (24 hrs / 180°)	16 N/25mm
Dimensional Stability	Excellent
Application Temperature	+5 to +25 °C
Service Temperature	-40 to +95 °C
Opacity Level	Medium
Printability	(eco)solvent, UV & latex

* equivalent to vertical exposure in Mid-European climate

Certifications

Fire Rating	EN 13501-1 (Class B)
-------------	----------------------

Warranty

iSee2 warrants our material for one (1) year from date of shipment. The shelf life of our material is dependent on storage conditions. We recommend that the end user stores the material in the original boxes (out of direct sunlight) from our factory. We also recommend to store our material at 21°C with 50% relative humidity. iSee2 only warrants our products to be free from defects in workmanship or defects in iSee2 material. We will replace or credit any material deemed defective. No acceptance or responsibility for loss, damage or expense implied or otherwise shall be assumed by the seller or manufacturer. User assumes all risk and liability in connection herewith. All data values quoted above are typical and should not be used to deem the product defective, if measured values are different.