# Metamark MD-i

## **Performance Calendered Digital Vinyl**



### **Product Description**

Metamark MD-i has been developed for medium term applications onto flat or simple curves, including vehicle graphics. The product features a 70 micron polymeric calendered film and Apex solvent adhesive, giving 5 years outdoor durability. MD-i utilises Metamark's distinctive coating technology to offer outstanding print and colour vibrancy, with Solvent, Eco Solvent, Latex and UV inks.

## **Printing and Handling**

- Suitable for use on Solvent, Eco Solvent, Latex and U.V. inkjet printers. Always perform a test print first.
- Ensure that the correct profiles and heater settings are used. Most profiles are available for download from www.metamark.co.uk.
- Ensure that the material has reached room temperature and a relative humidity of 50% before printing.
- Do not handle the face film directly and ensure it is free from dust and static.

#### Overlaminating

- Overlamination is recommended to prevent abrasion and to extend colour fastness.
- Allow the inks to cure before overlaminating, this is usually 24-48 hours. (Not applicable to HP Latex prints)
- The matched laminate for MD-i is MetaGuard MGi. For all other laminates the user should determine suitability.

#### **Application**

- Allow the inks to cure before cutting flush to the print, this is usually 24-48 hours. (Not applicable to HP Latex prints)
- Apply unstressed, in particular to curves and recesses. It is not suitable for application over rivets or complex recesses.
- Suitable for wet application. Always apply dry into recesses, or where the print is cut flush, to ensure best adhesion.
- Not recommended for use on low energy surfaces such as polypropylene. The user should determine suitability of substrate.
- Refer to www.metamark.co.uk for application guidelines.

Face Film		Roll Presentation		
70 micron nomi	nal	Roll sizes and net weights	760mm x 50m 1370mm x 50m	11kg 20kg
		Presentation	1600mm x 50m Face film outwards	23kg , on a 76mm core.
		Durability		
Permanent clear solvent-based acrylic 18gsm nominal 10N/25mm nominal 20N/25mm nominal Medium +5°C to +60°C		Shelf Life External weathering	2 years 5 years (International customers pleass contact your local Metamark partner for confirmation of durability). This refers to the unprinted vinyl. Referto ink manufacturer for durability of the finished product	
	,	Fire Rating Dimensional Stability	Class B. BS EN 135 <0.4mm (48h at 70	O°C on aluminium)
'Metamark Digital Vinyl' purple print 140 gsm nominal Layflat kraft paper with PE coating		Chemical Resistance	The unprinted film is resistant to mineral oils, fats and fuels, aliphatic solvents, mild acids, salt and alkali fo e.g. diesel oil, gasoline, paraffin, hydraulic oil, antifreeze, soap suds, e	
		Regulations	REACH and RoHS	, i ,
MD-i-100 MD-i-105	White Gloss Clear Gloss			
	70 micron nomi 49N/25mm MD 180% MD nomi  Permanent clear 18gsm nominal 10N/25mm nom 20N/25mm nom Medium +5°C to +60°C -30°C to +110°C  'Metamark Digit 140 gsm nomin Layflat kraft pap	18gsm nominal 10N/25mm nominal 20N/25mm nominal Medium +5°C to +60°C -30°C to +110°C  'Metamark Digital Vinyl' purple print 140 gsm nominal Layflat kraft paper with PE coating  MD-i-100 White Gloss	Polymeric Calendered PVC 70 micron nominal 49N/25mm MD / 47N/25mm TD nom. 180% MD nominal  Permanent clear solvent-based acrylic 18gsm nominal 10N/25mm nominal 20N/25mm nominal Medium +5°C to +60°C -30°C to +110°C  Shelf Life External weathering  Fire Rating Dimensional Stability Chemical Resistance  'Metamark Digital Vinyl' purple print 140 gsm nominal Layflat kraft paper with PE coating  MD-i-100  White Gloss	Polymeric Calendered PVC 70 micron nominal 49N/25mm MD / 47N/25mm TD nom. 180% MD nominal  Permanent clear solvent-based acrylic 18gsm nominal 10N/25mm nominal 20N/25mm nominal 20N/25mm nominal 49N/25mm nominal 20N/25mm nominal 20N/25mm nominal 20N/25mm nominal 49N/25mm nominal 5 years (Internation contact your local of confirmation of durn this refers to the unit of ink manufacture finished product. Fire Rating Dimensional Stability Chemical Resistance  Wetamark Digital Vinyl' purple print 140 gsm nominal Layflat kraft paper with PE coating  MD-i-100  White Gloss  Roll sizes and net weights 760mm x 50m 1370mm x 50m 1600mm x 50m Face film outwards  Shelf Life External weathering 5 years (Internation contact your local of the unit of the uni

D II D . . .:

Warranty: Metamark (UK) Limited warrants to its customers that graphics produced using Metamark Digital Media will remain in good condition without excessive fading or colour degradation for the specified life time of the ink used, when correctly stored, printed and applied in accordance with procedures outlined in the technical literature. If within the specified years of normal use Metamark DigitalVinyl becomes ineffective for its intended use, then Metamark will provide sufficient material to produce a new replacement marking, and will at its own discretion, contribute an allowance in additional material towards the costs involved in replacing the graphics. In all cases, the converteer is held fully responsible for storing, processing and applying the unconverted materials in accordance with Metamark's technical specifications. Metamark (UK) Limited will not be liable for any indirect or consequential loss or damage, and will not provide any allowance against improper usage, application accident, negligence, chemical damage or improper repair. Please Note: The above data is given in good faith to provide an indication of the performance of the product. Purchasers should consider the suitability of each product for its intended use and the purchaser assumes all risks in connection with such use. Seller shall not be liable for damages in excess of the purchase price of the product nor for incidental nor consequential loss.

# Metamark MD-i-A

### Performance Calendered Digital Vinvl with 'MetaScape' Adhesive



#### **Product Description**

Metamark MD-i-A features the 'MetaScape' adhesive system, offering ease of application by providing air with an exit route from under the graphic, making for faster, trouble-free application. With its 70 micron polymeric calendered film, and offering 5 years outdoor durability. MD-i-A is ideal for dry apply, medium term applications onto flat or simple curves including vehicle graphics. Suitable for printing with Solvent, Eco Solvent, Latex and UV inks.

#### Printing and Handling

- Suitable for use on Solvent, Eco Solvent, Latex and U.V. inkiet printers, Always perform a test print first.
- Ensure that the correct profiles and heater settings are used. Most profiles are available for download from www.metamark.co.uk.
- Ensure that the material has reached room temperature and a relative humidity of 50% before printing.
- Do not handle the face film directly and ensure it is free from dust and static.

#### Overlaminating

- Overlamination is recommended to prevent abrasion and to extend colour fastness.
- Allow the inks to cure before overlaminating, this is usually 24-48 hours.
- The matched laminate for MD-i-A is MetaGuard MGi. For all other laminates the user should determine suitability.

#### **Application**

Eaco Eilm

- Allow the inks to cure before cutting flush to the print, this is usually 24-48 hours. Suitable for dry application only.
- Apply to flat surfaces or simple curves. Apply unstressed. Not suitable for application over rivets or into deep recesses.
- Not recommended for use on low energy surfaces such as polypropylene. The user should determine suitability of substrate.
- Refer to www.metamark.co.uk for application guidelines.

race film		Finishes		
Face Film: Gauge:	Polymeric Calendered PVC 70 micron nominal	Finishes Available	MD-i-A	White Gloss
Tensile Strength	49N/25mm MD / 47N/25mm TD nom.	Roll Presentation		
Elongation at break	180% MD nominal	11011111001111111011		
		Roll sizes and net weights	760mm x 50m	10kg
Adhesive			1370mm x 50m 20kg	•
_			1600mm x 50m	24kg
Type	'MetaScape' permanent grey solvent- based acrylic with air channels.	Presentation	Face film outwards, on a 76mm core.	
Weight	18gsm nominal	Durability		
Adhesion to glass 20 mins	10N/25mm nominal	,		
Adhesion to glass 24 hour	20N/25mm nominal	Shelf Life	2 years	
Perceived tack	Medium	External weathering	5 years (Internation	al customers please
Application temperature	+5°C to +60°C		contact your local N	'
Service temperature	-30°C to +110°C		confirmation of dura	• /
D 1 1			This refers to the un	
Release Liner			to ink manufacturer	for durability of the
Print	'MataCaana' nurnla print	Fire Rating	finished product.	11_1.2007
Weight	'MetaScape' purple print 140 gsm nominal	Dimensional Stability	Class B. BS EN 13501-1:2007 <0.4mm (48h at 70°C on aluminium)	
Type	Structured layflat kraft paper with PE	Chemical Resistance	The unprinted film is resistant to	
туро	coating		mineral oils, fats and fuels, aliphatic	
	- County		solvents, mild acids	· •

Warranty: Metamark (UK) Limited warrants to its customers that graphics produced using Metamark Digital Media will remain in good condition without excessive fading or colour degradation for the specified life time of the ink used, when correctly stored, printed and applied in accordance with procedures outlined in the technical literature. If within the specified years of normal use Metamark DigitalVinyl becomes ineffective for its intended use, then Metamark will provide sufficient material to produce a new replacement marking, and will at its own discretion, contribute an allowance in additional material towards the costs involved in replacing the graphics. In all cases, the converter is held fully responsible for storing, processing and applying the unconverted materials in accordance with Metamark's technical specifications. Metamark (UK) Limited will not be liable for any indirect or consequential loss or damage, and will not provide any allowance against improper usage, application accident, negligence, chemical damage or improper repair. Please Note: The above data is given in good faith to provide an indication of the performance of the product. Purchasers should consider the suitability of each product for its intended use and the purchaser assumes all risks in connection with such use. Seller shall not be liable for damages in excess of the purchase price of the product nor for incidental nor consequential loss.

Regulations

#### Metamark (UK) Limited

e.g. diesel oil, gasoline, paraffin, hydraulic oil, antifreeze, soap suds, etc.

REACH and RoHS compliant

# **Metamark MD-i-AB**

## Performance Digital Vinyl with Grey 'MetaScape' Adhesive



### **Product Description**

Metamark MD-i-AB is a 70 micron polymeric calendered vinyl, with a grey pigmented adhesive to offer improved opacity, and prevent show-through on surfaces with a strong base colour, or for covering previous graphics.. The 'MetaScape' adhesive system, offering ease of application by providing air with an exit route from under the graphic, makes for faster, trouble-free application. MD-i-AB offers 5 years outdoor durability, and is ideal for medium term applications onto flat or simple curves including vehicle graphics. Suitable for printing with Solvent, Eco Solvent, Latex and UV inks.

## **Printing and Handling**

- Suitable for use on Solvent, Eco Solvent, Latex and U.V. inkiet printers. Always perform a test print first.
- Ensure that the correct profiles and heater settings are used. Most profiles are available for download from www.metamark.co.uk.
- Ensure that the material has reached room temperature and a relative humidity of 50% before printing.
- Do not handle the face film directly and ensure it is free from dust and static.

#### Overlaminating

- Overlamination is recommended to prevent abrasion and to extend colour fastness.
- Allow the inks to cure before overlaminating, this is usually 24-48 hours. (Not applicable to HP Latex prints)
- The matched laminate for MD-i-AB is MetaGuard MGi. For all other laminates the user should determine suitability.

#### Application-

- Allow the inks to cure before cutting flush to the print, this is usually 24-48 hours. (Not applicable to HP Latex prints)
- Apply unstressed, in particular to curves and recesses. It is not suitable for application over rivets or complex recesses.
- Suitable for wet application. Always apply dry into recesses, or where the print is cut flush, to ensure best adhesion.
- Not recommended for use on low energy surfaces such as polypropylene. The user should determine suitability of substrate.

**Finishes** 

• Refer to www.metamark.co.uk for application guidelines.

Face Film	
Face Film: Gauge: Tensile Strength Elongation at break	Polymeric Calendered PVC 70 micron nominal 49N/25mm MD / 47N/25mm TD nom. 180% MD nominal
Adhesive	
Type Weight Adhesion to glass 20 mins Adhesion to glass 24 hour Perceived tack Application temperature Service temperature	Permanent grey solvent-based acrylic 18gsm nominal 10N/25mm nominal 20N/25mm nominal Medium +5°C to +60°C -30°C to +110°C
Release Liner	
Print Weight Type	'MetaScape' purple print 140 gsm nominal Layflat kraft paper with PE coating

1 111101100			
Finishes Available	MD-i-AB	White Gloss	
Roll Presentation			
Roll sizes and net weights	760mm x 50m 1370mm x 50m	11kg 20kg	
Presentation	1600mm x 50m Face film outwards,	23kg on a 76mm core.	
Durability			
Shelf Life External weathering	2 years 5 years (International customers please contact your local Metamark partner for confirmation of durability). This refers to the unprinted vinyl. Refer to ink manufacturer for durability of the		
Fire Rating Dimensional Stability Chemical Resistance	finished product. Class B. BS EN 13501-1:2007 <0.4mm (48h at 70°C on aluminium) The unprinted film is resistant to mineral oils, fats and fuels, aliphatic solvents, mild acids, salt and alkali for e.g. diesel oil, gasoline, paraffin, hydraulic oil, antifreeze, soap suds, etc.		
Regulations	REACH and RoHS c		

Warranty: Metamark (UK) Limited warrants to its customers that graphics produced using Metamark Digital Media will remain in good condition without excessive fading or colour degradation for the specified life time of the ink used, when correctly stored, printed and applied in accordance with procedures outlined in the technical literature. If within the specified years of normal use Metamark DigitalVinyl becomes ineffective for its intended use, then Metamark will provide sufficient material to produce a new replacement marking, and will at its own discretion, contribute an allowance in additional material towards the costs involved in replacing the graphics. In all cases, the converter is held fully responsible for storing, processing and applying the unconverted materials in accordance with Metamark's technical specifications. Metamark (UK) Limited will not be liable for any indirect or consequential loss or damage, and will not provide any allowance against improper usage, application accident, negligence, chemical damage or improper repair. Please Note: The above data is given in good faith to provide an indication of the performance of the product. Purchasers should consider the suitability of each product for its intended use and the purchaser assumes all risks in connection with such use. Seller shall not be liable for damages in excess of the purchase price of the product nor for incidental nor consequential loss.

# Metamark MD-i-B

## Performance Digital Vinyl with Grey Adhesive



# **Product Description**

Metamark MD-i-B is a 70 micron polymeric calendered vinyl, with a grey pigmented adhesive to offer improved opacity, and prevent show-through. This results in more accurate colours when applied to surfaces with a strong base colour or for covering previous graphics. MD-i-B offers 5 years outdoor durability, and is ideal for medium term applications onto flat or simple curves including vehicle graphics. Suitable for printing with Solvent, Eco Solvent, Latex and UV inks.

#### **Printing and Handling**

- Suitable for use on Solvent, Eco Solvent, Latex and U.V. inkjet printers. Always perform a test print first.
- Ensure that the correct profiles and heater settings are used. Most profiles are available for download from www.metamark.co.uk.
- Ensure that the material has reached room temperature and a relative humidity of 50% before printing.
- Do not handle the face film directly and ensure it is free from dust and static.

#### **Overlaminating**

- Overlamination is recommended to prevent abrasion and to extend colour fastness.
- Allow the inks to cure before overlaminating, this is usually 24-48 hours.
- The matched laminate for MD-i-B is MetaGuard MGi. For all other laminates the user should determine suitability.

# Applicationi-

- Allow the inks to cure before cutting flush to the print, this is usually 24-48 hours.
- Apply unstressed, in particular to curves and recesses. It is not suitable for application over rivets or complex recesses.
- Suitable for wet application. Always apply dry into recesses, or where the print is cut flush, to ensure best adhesion.
- Not recommended for use on low energy surfaces such as polypropylene. The user should determine suitability of substrate.
- Refer to www.metamark.co.uk for application guidelines.

Face Film		Finishes
Face Film: Gauge:	Polymeric Calendered PVC 70 micron nominal	Finishes Available
Tensile Strength	49N/25mm MD / 47N/25mm TD nom.	<b>Roll Presentation</b>
Elongation at break	180% MD nominal	Roll sizes and net weights
Adhesive		rion oizee and not weighte
Type Weight	Permanent grey solvent-based acrylic 18gsm nominal	Presentation
Adhesion to glass 20 mins	10N/25mm nominal	Durability
Adhesion to glass 24 hour Perceived tack Application temperature Service temperature	20N/25mm nominal Medium +5°C to +60°C -30°C to +110°C	Shelf Life External weathering
Release Liner		
Print Weight Type	'Metamark Digital Vinyl' purple print 140 gsm nominal Layflat kraft paper with PE coating	Fire Rating Dimensional Stability Chemical Resistance

MD-i-B	White Gloss
760mm x 50m 1370mm x 50m 1600mm x 50m Face film outwards, o	11kg 20kg 23kg n a 76mm core.
2 years 5 years (International customers please contact your local Metamark partner for confirmation of durability). This refers to the unprinted vinyl. Refer to ink manufacturer for durability of the finished product. Class B. BS EN 13501-1:2007 <0.4mm (48h at 70°C on aluminium) The unprinted film is resistant to mineral oils, fats and fuels, aliphatic solvents, mild acids, salt and alkali for e.g. diesel oil, gasoline, paraffin,	
	760mm x 50m 1370mm x 50m 1600mm x 50m Face film outwards, o  2 years 5 years (International contact your local Met confirmation of durab This refers to the unpt to ink manufacturer for finished product. Class B. BS EN 13501 <0.4mm (48h at 70°C) The unprinted film is in mineral oils, fats and is solvents, mild acids, s

Warranty: Metamark (UK) Limited warrants to its customers that graphics produced using Metamark Digital Media will remain in good condition without excessive fading or colour degradation for the specified life time of the ink used, when correctly stored, printed and applied in accordance with procedures outlined in the technical literature. If within the specified years of normal use Metamark DigitalVinyl becomes ineffective for its intended use, then Metamark will provide sufficient material to produce a new replacement marking, and will at its own discretion, contribute an allowance in additional material towards the costs involved in replacing the graphics. In all cases, the converter is held fully responsible for storing, processing and applying the unconverted materials in accordance with Metamark's technical specifications. Metamark (UK) Limited will not be liable for any indirect or consequential loss or damage, and will not provide any allowance against improper usage, application accident, negligence, chemical damage or improper repair. Please Note: The above data is given in good faith to provide an indication of the performance of the product. Purchasers should consider the suitability of each product for its intended use and the purchaser assumes all risks in connection with such use. Seller shall not be liable for damages in excess of the purchase price of the product nor for incidental nor consequential loss.

# Metamark MDiG

## Performance Vinyl with MetaGlide® air release



### **Product Description**

Metamark MDiG features the MetaGlide® next generation air release system offering improved all round handling. With its micro structured air release liner, lift and reapply MetaGlide® graphics with a smooth clean peel that prevents damage to the graphic. MetaGlide® system offers exceptional layflat printability. Prints can stay stored or loosely rolled confidently without tunnelling or delamination. Metamark's 70 micron white face film with its distinctive coating technology produces outstanding print performance on Solvent, Eco Solvent, UV and Latex printers.

#### **Printing and Handling**

- Suitable for use on Solvent, Eco Solvent, Latex and U.V. inkjet printers. Always perform a test print first.
- Ensure that the correct profiles and heater settings are used. Most profiles are available for download from www.metamark.co.uk.
- Ensure that the material has reached room temperature and a relative humidity of 50% before printing.
- Do not handle the face film directly and ensure it is free from dust and static.

#### **Overlaminating**

- Overlamination is recommended to prevent abrasion and to extend colour fastness.
- Allow the inks to cure before overlaminating, this is usually 24-48 hours.
- The matched laminate for MDiG is MetaGuard MGi. For all other laminates the user should determine suitability.

#### **Application**

- Allow the inks to cure before cutting flush to the print, this is usually 24-48 hours. Suitable for dry application only.
- Apply to flat surfaces or simple curves. Apply unstressed. Not suitable for application over rivets or into deep recesses.
- Not recommended for use on low energy surfaces such as polypropylene. The user should determine suitability of substrate.
- Refer to www.metamark.co.uk for application guidelines.

Face Film		Finishes			
Face Film: Gauge:	Polymeric Calendered PVC 70 micron nominal	Finishes Available	MDiG-100	White Gloss	
Tensile Strength	49N/25mm MD / 47N/25mm TD nom.	Roll Presentation			
Elongation at break	180% MD nominal	Roll sizes	760mm x 25m / 50	)m	
Adhesive		UOII 21762	760mm x 25m / 50m 1370mm x 25m / 50m		
Туре	MetaGlide® Air Release Permanent Solvent-Based Adhesive.	Presentation	1600mm x 25m / 5 Face film outwards	• • • • • • • • • • • • • • • • • • • •	
Weight	19gsm nominal	Durability			
Adhesion to glass 20 mins Adhesion to glass 24 hour Perceived tack Application temperature Service temperature	10N/25mm nominal 20N/25mm nominal Medium +5°C to +60°C -30°C to +110°C	Shelf Life External weathering	2 years 5 years (International customers pleace contact your local Metamark partner confirmation of durability). This refers to the unprinted vinyl. Re		
Release Liner				r for durability of the	
Print Weight Type	'MetaGlide®' purple print 140 gsm nominal Structured layflat kraft paper with PE coating	Fire Rating Dimensional Stability Chemical Resistance Regulations	finished product. Class B. BS EN 13501-1:2007 <0.4mm (48h at 70°C on aluminium) The unprinted film is resistant to mineral oils, fats and fuels, aliphatic solvents, mild acids, salt and alkali for e.g. diesel oil, gasoline, paraffin, hydraulic oil, antifreeze, soap suds, etc. REACH and RoHS compliant		

Warranty: Metamark (UK) Limited warrants to its customers that graphics produced using Metamark Digital Media will remain in good condition without excessive fading or colour degradation for the specified life time of the ink used, when correctly stored, printed and applied in accordance with procedures outlined in the technical literature. If within the specified years of normal use Metamark DigitalVinyl becomes ineffective for its intended use, then Metamark will provide sufficient material to produce a new replacement marking, and will at its own discretion, contribute an allowance in additional material towards the costs involved in replacing the graphics. In all cases, the converter is held fully responsible for storing, processing and applying the unconverted materials in accordance with Metamark's technical specifications. Metamark (UK) Limited will not be liable for any indirect or consequential loss or damage, and will not provide any allowance against improper usage, application accident, negligence, chemical damage or improper repair. Please Note: The above data is given in good faith to provide an indication of the performance of the product. Purchasers should consider the suitability of each product for its intended use and the purchaser assumes all risks in connection with such use. Seller shall not be liable for damages in excess of the purchase price of the product nor for incidental nor consequential loss.