Metamark MiA[™] Series

Interior Architectural Films

Product Description

Metamark MiA [™] Interior Architectural films offer a range of finishes for interior transformations. The range includes finishes with authentic textures and tones. They are hardwearing, repairable, and easy to maintain and clean. Our films can be installed on a wide range of interior surfaces and the process is fast, clean, quiet and odour-free. The visual transformation is immediate and dramatic. Metamark Interior Architectural films can be installed by professionals used to handling pressure-sensitive self-adhesive materials. Applications include kitchen refurbishment, doors, lift doors, furniture, and washroom partitions, for commercial and domestic use. The engineered multilayer films have a clear hardwearing topcoat which also gives the product a quality feel, and an air release adhesive for ease of installation. They offer up to 10 years interior durability.

Features & Benefits

- Premium interior architectual films.
- Advanced dual layer material.
- MetaScape[®] Adhesive System allowing ease of application.
- Authentic textured finishes.
- UKCA and CE approved.
- Up to 10 years interior durability.

| Face Film | | Finishes | | | | | |
|--|---|---|---|---|--|--|--|
| Face Film Gauge (ISO 2286-3) | Conformable Polymeric PVC 165 - 250 micron nominal | Finishes Available | Range of Natural Wood, Stone, Metal & Soft Matt | | | | |
| Elongation at break | 220% MD nominal | Roll Presentation | | | | | |
| Adhesive | | Roll Widths | 1.22m | | | | |
| Туре | MetaScape [®] permanent solvent-based acrylic with air channels. | Roll Lengths | 50m | | | | |
| Adhesion 24 hour | 12N/25mm nominal | Durability | | | | | |
| Application temperature Service temperature | +10°C to +35°C -30°C to +110°C | Shelf Life | 2 years. (10-20°C and 50% R.H). Store away from direct sunlight in original packaging. | | | | |
| Release Liner | | Durability | up to 10 years under no direct UV | | | | |
| Print | 'MiA MetaScape' purple print | · | exposure. | | | | |
| Weight | 140 gsm nominal | Fire Rating | Class B - BS EN 13501-1:2018 | | | | |
| Туре | Structured micro channel PE layflat | Chemical Resistance | Resistant to mineral oils, fats and fuels, aliphatic solvents, mild acids, salt and alkali for e.g. diesel oil, gasoline, paraffin, hydraulic oil, antifreeze, soap suds etc. | | | | |
| | | Regulations | UKCA, CE, REACH & RoHS compliant | | | | |
| Application | | | | | | | |
| Successful application requires the necessary techniques. Refer to www.metamark.co.uk for application guidelines. Use a dry application method. If multiple rolls are needed, ensure they are from the same batch. | | Use water based primer if needed. Films should be applied in the same direction. Not suitable for use on corrosion susceptible metals, non-sealed concrete, stone or drywall (inc skim coat). | | | | | |
| | | | | Fill any holes or gouges with non water-based filler. | | The user should determine suitability. | |

MetaSure® Warranty

Metamark (UK) Limited warrants to its customers that its films are manufactured to be free of material defect, and will meet the specified lifetime of the product, when correctly stored, processed, and installed in accordance with procedures outlined in the technical literature. If within the specified years of normal use MetaCast[®] films become ineffective for its intended use, then Metamark will provide sufficient material to produce a new replacement marking, and will at its own discretion, contribute an allowance in additional material towards the costs involved in replacing the graphics. In all cases, the converter is held fully responsible for storing, processing and applying the unconverted materials in accordance with Metamark's technical specifications. Metamark (UK) Limited will not be liable for any indirect or consequential loss or damage, and will not provide any allowance against improper usage, application accident, negligence, chemical damage or improper repair. The above data is given in good faith to provide an indication of the performance of the product. Purchasers should consider the suitability of each product for its intended use and the purchaser assumes all risks in connection with such use. Seller shall not be liable for damages in excess of the purchase price of the product nor for incidental nor consequential loss.

Metamark (UK) Limited

sales@metamark.co.uk www.metamark.co.uk

